

Appln. No. 10/05,913  
Response dated January 7, 2005  
Reply to Office Action of October 20, 2004

**BEST AVAILABLE COPY**

**AMENDMENT TO CLAIMS**

**WHAT IS CLAIMED IS:**

1. (canceled)
2. (canceled)
3. (canceled)
4. (canceled)
5. (canceled)
6. (canceled)
7. (currently amended) A composition comprising a stable polyurethane latex having a mean volume average particle size of not greater than about 1 micron and a solids content of at least 45 percent by weight, wherein the polyurethane latex contains units formed from a chain-extending reagent selected from the group consisting of water, diamines, and alcohol monoamines and wherein the latex is stabilized by a surfactant consisting ~~essentially~~ of an external anionic surfactant.
8. (canceled)
9. (previously presented) The composition of Claim 7 wherein the polyurethane latex has a solids content of at least 55 percent by weight, wherein the chain-extending reagent is selected from the group consisting of piperazine and water, and wherein the latex contains not more than 0.1 weight percent solvent.
10. (canceled)
11. (canceled)
12. (canceled)

Appln. No. 10/05,913  
Response dated January 7, 2005  
Reply to Office Action of October 20, 2004

13. (previously presented) The composition of Claim 7 wherein the external anionic surfactant is a sulfate of an ethoxylated phenol, an alkali metal fatty acid salt, an alkali metal lauryl sulfate, an amine lauryl sulfate, an alkali metal alkylbenzene sulfonate, an amine alkylbenzene sulfonate, or an alkali metal soap of a modified resin and wherein the latex contains no solvent and wherein the chain extending reagent includes water.

14. (canceled)

15. (new) A composition comprising a stable polyurethane latex having a mean volume average particle size of not greater than about 1 micron and a solids content of at least 45 percent by weight, wherein the polyurethane latex consists of a non-self-emulsifying prepolymer and contains units formed from a chain-extending reagent selected from the group consisting of water, diamines, and alcohol monoamines and wherein the latex is stabilized by an external anionic surfactant.

16. (new) The composition of Claim 15, wherein the latex is stabilized solely by an external anionic surfactant.